

## Material Density Chart

Material	Density (Loose)	Material	Density (Loose)
Ashes	1,100 lb/yd <sup>3</sup>	Gypsum–Crushed	2,700 lb/yd <sup>3</sup>
Caliche	2,100 lb/yd <sup>3</sup>	Kaolin	1,730 lb/yd <sup>3</sup>
Cement–Portland	2,550 lb/yd <sup>3</sup>	Limestone–Broken	2,600 lb/yd <sup>3</sup>
Cereals–Wheat, Bulk	1,300 lb/yd <sup>3</sup>	Salt–Coarse	1,350 lb/yd <sup>3</sup>
Clay (natural bed)	2,800 lb/yd <sup>3</sup>	Sand–Dry	2,700 lb/yd <sup>3</sup>
Clay (Dry Lumps)	1,820 lb/yd <sup>3</sup>	Sand–Wet	3,500 lb/yd <sup>3</sup>
Clay (Wet Lumps)	2,700 lb/yd <sup>3</sup>	Sand with gravel–Dry	2,900 lb/yd <sup>3</sup>
Clay with Gravel (Dry)	2,700 lb/yd <sup>3</sup>	Sand with gravel–Wet	3,400 lb/yd <sup>3</sup>
Clay with Gravel (Wet)	3,080 lb/yd <sup>3</sup>	Sandstone–Broken	2,550 lb/yd <sup>3</sup>
Coal–Anthracite(Broken)	1,850 lb/yd <sup>3</sup>	Sawdust	550 lb/yd <sup>3</sup>
Coal–Bituminous(Broken)	1,400 lb/yd <sup>3</sup>	Shale	2,100 lb/yd <sup>3</sup>
Coke	875 lb/yd <sup>3</sup>	Silage	865 lb/yd <sup>3</sup>
Earth–Dry, Packed	2,550 lb/yd <sup>3</sup>	Slag–Broken	2,950 lb/yd <sup>3</sup>
Earth–Wet, Excavated	2,700 lb/yd <sup>3</sup>	Snow–Dry	400 lb/yd <sup>3</sup>
Earth, Loam	2,100 lb/yd <sup>3</sup>	Snow–Wet	600 lb/yd <sup>3</sup>
Garbage–Wet	1,350 lb/yd <sup>3</sup>	Stone–Crushed	2,700 lb/yd <sup>3</sup>
Granite–Broken	2,800 lb/yd <sup>3</sup>	Sugar–Raw, Refined	1,750 lb/yd <sup>3</sup>
Gravel–Dry	2,550 lb/yd <sup>3</sup>	Topsoil	1,600 lb/yd <sup>3</sup>
Graveled Sand	3,250 lb/yd <sup>3</sup>	Wood Chips (Dry)	600 lb/yd <sup>3</sup>
Gravel–Dry (½” to 2”)	2,850 lb/yd <sup>3</sup>	Wood Chips (Wet)	900 lb/yd <sup>3</sup>
Gravel–Wet (½” to 2”)	3,375 lb/yd <sup>3</sup>		

\*Actual material density may vary from these standard values.

Corporate Office:  
330-678-2511  
800-321-2348  
Fax: 330-678-0859

Northwest:  
360-474-1940  
Fax: 360-474-9941

[www.acs-coupler.com](http://www.acs-coupler.com)